

Technical data sheet
Membrana mdm[®] Ventia Titanium Plus - 25th anniversary

Characteristic	Test method	Unit	Result	Tolerance	
				Min.	Max.
Lenght	EN 1848 -2	m	50	0	+0,5
Width	EN 1848 -2	m	1,5	-0,005	+0,005
Straightness	EN 1848 -2	-	Pass	-	-
Mass per unit area	EN 1848 -2	g/m ²	190	-15	+15
Thickness	EN 1848 -2	mm	0,75	-0,15	+0,15
Reaction to fire (free-hanging)	EN 11925-2	class	E-d2	-	-
Resistance to water penetration	EN 1928 A	class	W1	-	-
Water vapour transmission Properties	EN ISO 12572 C	m	0,020	-0,005	+0,02
Resistance to penetration of air	EN 12114	m ³ /(m ² x h x 50 Pa)	Max 0,05	-	-
Tensile properties: Maximum tensile force	EN 12311-1	N/50mm	MD 415	-25%	+25%
			CD 300	-35%	+35%
Tensile properties: elongation	EN 12311-1	%	MD 75	-45	+45
			CD 110	-55	+55
Resistance to tearing (nail shank)	EN 12310-1	N	MD 250	-45%	+45%
			CD 300	-35%	+35%
Dimensional Stability	EN 1107-2	%	2	-	-
Stability at low temperature	EN 1109	°C	-40	-	-
Artificial ageing by long term exposure to the combination Of UV radiation and elevated Temperatura and heat (80°C)	Elongation EN 13859-1 annex C	%	MD 50	-25	+25
			CD 60	-25	+25
	Tensile strength EN 13859-1 annex C	N/50mm	MD 370	-25%	+25%
			CD 210	-25%	+25%
Resistance to water penetration EN 13859-1 annex C	class	W1	-	-	
Water vapour transmission 23°C/85%RH	Lyssy	g/m ² x 24h	1400	-250	+250
Water vapour transmission 38°C/90%RH	Lyssy	g/m ² x 24h	2900	-400	+400

 Bielsko-Biała,
 (Place and date of issue)

9.01.2020

 VAT No. PL5482614481
 Registered in Poland, KRS No. 0000354101
 Share capital: 992 500 PLN

 Bank Handlowy w Warszawie S.A., SWIFT: CITIPLPX
 IBAN: PL 67 1030 1508 0000 0008 1613 6008 (PLN)
 IBAN: PL 23 1030 1508 0000 0008 1613 6024 (EUR)
 IBAN: PL 98 1030 1508 0000 0008 1613 6032 (USD)